

Ebetong AB  
Jupitervägen 10  
19443 Upplands Väsby  
SWEDEN

Eurofins Product Testing A/S  
Smedeskovvej 38  
8464 Galten  
Denmark

CustomerSupport@eurofins.com  
www.eurofins.com

# VOC TEST REPORT

## Byggvarubedömningen

16 June 2025

### 1 Sample Information

Sample name	Ebetong 4517 2.0
Batch no.	Nbr 071
Stated production date	15/04/2025
Product type	Levelling compound, cement based
Sample reception	22/04/2025

### 2 Brief Evaluation of the Results

Regulation or protocol	Conclusion	Version of regulation or protocol
Byggvarubedömningen	Recommended	Byggvarubedömningen's criteria for chemical content and lifecycle aspects, version 7.4 (2024-09-02), section 6.

Full details based on the testing and direct comparison with limit values is available in the following pages. Conclusion is only based on the VOC emission performance of the product as required in section 6.1, 6.2, other factors may lead to an alternative overall evaluation of the product.



Isabella B. Larsen  
Analytical Service Manager



Janne Rothmann Norup  
Analytical Service Manager

## Table of contents

<b>1</b>	<b>Sample Information</b>	<b>1</b>
<b>2</b>	<b>Brief Evaluation of the Results</b>	<b>1</b>
<b>3</b>	<b>Applied Test Methods</b>	<b>3</b>
3.1	General Test References	3
3.2	Specific Laboratory Sampling and Analyses	3
<b>4</b>	<b>Test Parameters, Sample Preparation and Deviations</b>	<b>4</b>
4.1	VOC Emission Chamber Test Parameters	4
4.2	Preparation of the Test Specimen	4
4.3	Picture of Sample	4
4.4	Deviations from Referenced Protocols and Regulations	5
4.5	Air Samplings from the Test Chamber	5
<b>5</b>	<b>Results</b>	<b>6</b>
5.1	VOC Emission Test Results after 28 Days	6
<b>6</b>	<b>Summary and Evaluation of the Results</b>	<b>7</b>
6.1	Comparison with Limit Values of Byggvarubedömningen	7
<b>7</b>	<b>Appendices</b>	<b>8</b>
7.1	Chromatogram of VOC Emissions after 28 Days	8
7.3	Sampling Report	9
7.4	How to Understand the Results	11
7.6	Applied LCI Values	12
7.7	Qualitative Description of VOC Emission Test	13
7.8	Quality Assurance	14
7.9	Accreditation	15
7.10	Uncertainty of the Test Method	15
7.11	Decision Rules	15
7.12	Version History	15

### 3 Applied Test Methods

#### 3.1 General Test References

Regulation, protocol or standard	Version	Reporting limit VOC [ $\mu\text{g}/\text{m}^3$ ]	Calculation of TVOC	Combined uncertainty $\alpha$ [RSD(%)]
EN 16516	2017 + A1:2020	5	Toluene equivalents	22%
ISO 16000 -3 -6 -9 -11	2021-2024 depending on part	2	Toluene equivalents	22%
ASTM D5116-10	2017	-	-	-
Byggvarubedömningen	Byggvarubedömningen's criteria for chemical content and lifecycle aspects, version 7.4 (2024-09-02), section 6.	2	Toluene equivalents	22%

#### 3.2 Specific Laboratory Sampling and Analyses

Procedure	External Method	Internal S.O.P.	Quantification limit / sampling volume	Analytical principle	Uncertainty $\alpha$ [RSD(%)]
Sample preparation	ISO 16000-11:2024, EN 16516:2017+A1:2020, AgBB:2024, EMICODE:2022	71M549810	-	-	-
Emission chamber testing	ISO 16000-9:2024, EN 16516:2017+A1:2020	71M549811	-	Chamber and air control	-
Sampling of VOC	ISO 16000-6:2021, EN 16516:2017+A1:2020	71M549812	5 L	Tenax TA	-
Analysis of VOC	ISO 16000-6:2021, EN 16516:2017+A1:2020	71M542808B	1 $\mu\text{g}/\text{m}^3$	ATD-GC/MS	10%
Sampling of aldehydes	ISO 16000-3:2022, EN 16516:2017+A1:2020	71M549812	35 L	DNPH	-
Analysis of aldehydes	ISO 16000-3:2022, EN 16516:2017+A1:2020	71M548400	3-6 $\mu\text{g}/\text{m}^3$	HPLC-UV	10%

## 4 Test Parameters, Sample Preparation and Deviations


### 4.1 VOC Emission Chamber Test Parameters

Parameters	Value	Sample Conditions	Value
Chamber volume, V[L]	119	Date and time of unpacking and start of sample preparation	12/05/2025 - 12:30
Air change rate, n[h <sup>-1</sup> ]	0.5	Preconditioning period	-
Air Velocity [m/s]	0.1	Chamber test period	12/05/2025 - 09/06/2025
Area specific ventilation rate, q [m/h or m <sup>3</sup> /m <sup>2</sup> /h]	1.25	Analytical test period	12/05/2025 - 13/06/2025
Relative humidity of supply air, RH [%]	50 ± 3	Exposed sample area [m <sup>2</sup> ]	0.0476
Temperature of supply air, T [°C]	23 ± 1	Loading factor [m <sup>2</sup> /m <sup>3</sup> ]	0.40
Background concentration of individual VOC's [µg/m <sup>3</sup> ]	< 2	Test scenario	Flooring or ceiling
Background concentration of TVOC [µg/m <sup>3</sup> ]	< 20		

### 4.2 Preparation of the Test Specimen

The sample was mixed homogeneously, 510 g material in 190 g water. A part of the mixture was spread onto a glass plate and drawn off over a model giving a 3 mm thick and uniform layer.

### 4.3 Picture of Sample



The results are only valid for the tested sample(s).

This report may only be copied or reprinted in its entirety, parts of it only with a written acceptance by Eurofins.

#### 4.4 Deviations from Referenced Protocols and Regulations

No deviations from the referenced test methods were observed.

#### 4.5 Air Samplings from the Test Chamber

Sampling media	Day (yyyy-mm-dd)	Time (hh:mm)	Volume [L]
28 Day, DNPH silicagel	2025-06-09	10:46 - 12:36	37
28 Day-Res, DNPH silicagel	2025-06-09	10:47 - 12:36	36
28 Day, Tenax TA	2025-06-09	10:48 - 11:47	5.2
28 Day-Res, Tenax TA	2025-06-09	11:47 - 12:37	2.3

## 5 Results

### 5.1 VOC Emission Test Results after 28 Days

	CAS No.	Retention time [min]	ID-Cat	Specific Conc. [µg/m³]	Toluene eq. [µg/m³]	Specific SER [µg/(m²·h)]	R <sub>EU</sub>
<b>VOC with LCI</b>							
None determined							
<b>VOC without LCI</b>							
None determined							
<b>Sum of VOC without LCI</b>				< 5	< 5	< 7	
<b>VVOC compounds</b>							
None determined							
<b>TVVOC</b>				< 5	< 5	< 7	
<b>SVOC compounds</b>							
None determined							
<b>TSVOC</b>				< 5	< 5	< 7	
<b>Carcinogens</b>							
<b>Total carcinogens</b>				< 1	< 1	< 2	
<b>Aldehydes</b>							
Formaldehyde	50-00-0		1	< 3		< 4	
Acetaldehyde	75-07-0		1	3.9		4.9	
Propionaldehyde	123-38-6		1	< 3		< 4	
Butyraldehyde	123-72-8		1	< 3		< 4	
Acrolein *	107-02-8		1	< 5		< 7	
2-Butenal *	123-73-9		1	< 5		< 7	
Glutaraldehyde *	111-30-8		1	< 3		< 4	
<b>R-values</b>							0
<b>TVOC</b>				< 5	< 5	< 7	

The results are only valid for the tested sample(s).

This report may only be copied or reprinted in its entirety, parts of it only with a written acceptance by Eurofins.

## 6 Summary and Evaluation of the Results


### 6.1 Comparison with Limit Values of Byggvarubedömningen

Parameter	Test after 28 days			
	Concentration $\mu\text{g}/\text{m}^3$	To be Avoided $\mu\text{g}/\text{m}^3$	Limit Value Accepted $\mu\text{g}/\text{m}^3$	Limit Value Recommended $\mu\text{g}/\text{m}^3$
<b>TVOC [EN 16516]</b>	< 5	> 1000	$\leq 1000$	$\leq 300$
<b>Formaldehyde</b>	< 3	$\geq 60 \mu\text{g}/\text{m}^3$	< 60	
<b>R-value</b>	0	> 1		$\leq 1$
<b>Any individual carcinogens</b>	< 1	$\geq 1 \mu\text{g}/\text{m}^3$	< $1 \mu\text{g}/\text{m}^3$	
<b>Single VOCs with EU-LCI</b>	Comply	> EU-LCI	$\leq$ EU-LCI	

Limit values are only based on the VOC emission performance of the product as required in section 6.1, 6.2, other factors may lead to an alternative overall evaluation of the product.

## 7 Appendices


### 7.1 Chromatogram of VOC Emissions after 28 Days



The results are only valid for the tested sample(s).


This report may only be copied or reprinted in its entirety, parts of it only with a written acceptance by Eurofins.

### 7.3 Sampling Report

<b>Combined Sampling Report and Chain of Custody</b>	
<b>Name of applicant</b> <small>(name, company, phone)</small>	Stefan Ingelin Ebetong AB +46 738 01 01 98
Product Information	
<b>Name of the product:</b> Ebetong 4517 2.0	<b>Product Type:</b> Levelling compound, cement based
<b>Batch No:</b> Nbr 071	<b>Article No:</b> 4517 2.0
<b>Model/Program/ Series:</b>	<b>Manufacturer</b> <small>(Company, Address, Stamp)</small> Ebetong AB Jupitervägen 10 19443 Upplands Väsby
Production & Sampling information	
<b>Production date:</b> 4/15/2025	<b>Sampling Date:</b> 4/15/2025
<b>Time:</b>	<b>Time:</b>
<b>Place of sampling</b> <small>(if deviation from the manufacture)</small>	<b>Production site</b>
	<b>Sample is taken from:</b> <input checked="" type="checkbox"/> ongoing production <input type="checkbox"/> stocks <input type="checkbox"/> retained sample
	<b>Number of samples:</b> 1
<b>Person in charge of sampling:</b> <small>(Name, company, telephone)</small>	<b>Signature of sample collector:</b>
<b>Where has the product been stored prior to sampling?</b> <small>Place of storage</small>	<b>How has the product been stored prior to sampling?</b> <small>Packaging material</small>
<input checked="" type="checkbox"/> production <input type="checkbox"/> store <input type="checkbox"/> miscellaneous	<input type="checkbox"/> open <input type="checkbox"/> in the stack <input checked="" type="checkbox"/> wrapped up
<b>Specifics</b> (possible negative influences by air contamination where sample was taken, by petrol emissions, by solvent emissions from production, any other uncertainties, questions, etc).	
Cut edges (identification of cut edges when present and identification of new surfaces and surface to be exposed in the emission test).	
Confirmation from the applicant	
Here with the signer confirms the correctness of the data given above. The sample was selected, drawn and packed personally in accordance with the instructions for the taking of the samples.	
<b>Date:</b> 2025-04-16	<b>Signature:</b> Leif Lindqvist 

The results are only valid for the tested sample(s).

This report may only be copied or reprinted in its entirety, parts of it only with a written acceptance by Eurofins.

	(stamp)		
<b>Chain of custody</b>			
Whenever the sample is handed over, please fill out the below information			
Handed over between:	Initials + Signature	Date + Time	Condition
Handed over by: Erik L Wijkander		Date:2025-04-16 UTC+2h:12.07.00	Responsible for Truck loading Ebetong warehose facilites
Handed over by Dachser Sweden AB			
Handed over by			
Handed over by			
Handed over by			
Handed over by			
Laboratory receiving details (date condition of package and samle, assigned lab no.):			
Receptionist, Eurofins Product Testing A/S:		Signature of receptionist:	

## 7.4 How to Understand the Results

### 7.4.1 Acronyms Used in the Report

<	Means less than
>	Means bigger than (Tube/GC-MS overload)
*	Not a part of our accreditation
α	Please see section regarding uncertainty in the Appendices.
§	Deviation from method. Please see deviation section
a	The method is not optimal for very volatile compounds. For these substances smaller results and a higher measurement uncertainty cannot be ruled out.
b	The component originates from the substrate and is thus removed.
c	The results have been corrected by the emission from substrate.
d	Very polar organic compounds are not suitable for reliable quantification using tenax TA adsorbent and HP-5 GC column. A high degree of uncertainty must be expected.
e	The component may be overestimated due to contribution from the system
SER	Specific emission rate.

### 7.4.2 Explanation of ID Category

#### Categories of Identity:

- 1: Identified by comparison with a mass spectrum obtained from library and supported by other information and quantified through specific calibration.
- 2: Identified by comparison with a mass spectrum obtained from library and supported by other information. Quantified as toluene equivalent.
- 3: Identified with a lower match by comparison with a mass spectrum obtained from a library. Quantified as toluene equivalent.
- 4: Not identified, quantified as toluene equivalent.

## 7.6 Applied LCI Values

### 7.6.1 LCI/NIK Values for Compounds found after 28 Day Measurements

Compound	CAS No.	LCI [ $\mu\text{g}/\text{m}^3$ ]
Acetaldehyde	75-07-0	300

## 7.7 Qualitative Description of VOC Emission Test

### 7.7.1 Test Chamber

The test chamber is made of stainless steel. A multi-step air clean-up is performed before loading the chamber, and a blank check of the empty chamber is performed.

The chamber operation parameters are as described in the test method section (EN 16516, ISO 16000-9, internal method no.: 71M549811).

### 7.7.2 Expression of the Test Results

All test results are calculated as specific emissions rate, and as extrapolated air concentration in the European Reference Room (EN 16516, AgBB, EMICODE, M1 and Indoor Air Comfort).

### 7.7.3 Testing of Carcinogenic VOCs

The emission of carcinogens (EU Categories C1A and C1B, as per European law) is tested by drawing sample air from the test chamber outlet through Tenax TA tubes after the specified duration of storage in the ventilated test chamber. Analysis is performed by ATD-GC/MS (automated thermal desorption coupled with gas chromatography and mass spectroscopy using 30 m HP-5 (slightly polar) column with 0.25 mm ID and 0.25 µm film, Agilent) (EN 16516, ISO 16000-6, internal methods no.: 71M549812 / 71M542808B).

All identified carcinogenic VOCs are listed; if a carcinogenic VOC is not listed then it has not been detected. Quantification is performed using the TIC signal and authentic response factors, or the relative response factors relative to toluene for the individual compounds.

This test only covers substances that can be adsorbed on Tenax TA and can be thermally desorbed. If other emissions occur, then these substances cannot be detected (or with limited reliability only).

### 7.7.4 Testing of VOC, SVOC and VVOC

The emissions of volatile organic compounds are tested by drawing sample air from the test chamber outlet through Tenax TA tubes after the specified duration of storage in the ventilated test chamber. Analysis is performed by ATD-GC/MS using HP-5 column (30 m, 0.25mm ID, 0.25µm film) (EN 16516, ISO 16000-6, internal methods no.: 71M549812 / 71M542808B).

All single substances that are listed with a LCI/NIK value in the latest publications (hereafter referred to as target compounds) are identified if present. All other appearing VOCs are identified as far as possible. Quantification of target compounds is done using the TIC signal and authentic response factors, or the relative response factors relative to toluene. For certain compound groups, which differ significantly in chemistry from toluene, quantification is performed relative to a representative member of the group for more accurate and precise results. This can include quantification of for example glycols and acids. In addition to that, all results are also expressed in toluene equivalents. All non-target compounds, as well as all non-identified substances, are quantified in toluene equivalents.

The results of the individual substances are calculated in three groups depending on their retention time when analyzing using a non-polar column (HP-1):

- Volatile Organic Compounds (VOC) are defined as: All substances eluting between and including n-hexane (n-C6) and n-hexadecane (n-C16)
- Semi-Volatile Organic Compounds (SVOC) are defined as: All substances eluting after n-hexadecane (n-C16) and before and including n-docosane (n-C22)
- Very Volatile Organic Compounds (VVOC) are defined as: All substances eluting before n-hexane (n-C6).

Total Volatile Organic Compounds (TVOC) is calculated by summation of all individual VOCs with a

The results are only valid for the tested sample(s).

This report may only be copied or reprinted in its entirety, parts of it only with a written acceptance by Eurofins.

concentration  $\geq 5 \mu\text{g}/\text{m}^3$ . The TVOC can be expressed either in toluene equivalents as defined in EN 16516 and similar to ISO 16000-6, or as the sum of concentrations using specific or relative response factors. In the case of summation of concentrations using authentic or relative response factors, the toluene equivalent is applied to all non-target and non-identified VOCs before summing up. Compounds regarded as VOC in line with the above definition but elute before n-C6 or after n-C16 on the HP-5 column are treated as VOC, and are thus added to the TVOC.

Total Semi-Volatile Organic Compounds (TSVOC) is calculated by the summation of all individual SVOCs expressed in toluene equivalents with a concentration  $\geq 5 \mu\text{g}/\text{m}^3$ , as defined in EN 16516. VOCs that are regarded as VOC in line with the above definition, but elute after n-C16 in this test, are not added to the TSVOC.

Total Very Volatile Organic Compounds (TVVOC) is calculated by the summation of all individual VVOCs with a concentration  $\geq 5 \mu\text{g}/\text{m}^3$  and expressed in toluene equivalents. VOCs that are regarded as VOC in line with the above definition, but elute before n-C6 in this test, are not added to the TVVOC.

This test only covers substances which can be adsorbed on Tenax TA and can be thermally desorbed. If emissions of substances outside these specifications occur then these substances cannot be detected (or with limited reliability only).

### 7.7.5 Calculation of R Values with LCI Lists

The concentrations of detected compounds  $\geq 5 \mu\text{g}/\text{m}^3$  are divided by their respective LCI/NIK value (if defined in the given publication). The sum of the quotients gives the R value, which can be mathematically expressed:

$$R = \sum_{i=1}^n \left( \frac{c_i}{\text{NIK}_i} + \dots + \frac{c_n}{\text{NIK}_n} \right)$$

This R value is calculated, depending on the purpose of this test, for the European LCI list, for the German LCI/NIK list ( $R_D$ ), and/or for the Belgian LCI list ( $R_B$ ).

All VOCs without published LCI/NIK value and concentration  $\geq 5 \mu\text{g}/\text{m}^3$  are summed up as sum of VOCs without LCI/NIK if required by the standard or protocol.

### 7.7.6 Testing of Aldehydes

The presence of aldehydes is tested by drawing air samples from the test chamber outlet through DNPH-coated silicagel tubes after the specified duration of storage in the ventilated test chamber. Analysis is performed by solvent desorption and subsequently by HPLC and UV-/diode array detection (EN 16516, ISO 16000-3, VDI 3862 Blatt 3, internal methods no.: 71M549812 / 71M548400).

The absence of formaldehyde and other aldehydes is stated if UV detector response at the specific wavelength is lacking at the specific retention time in the chromatogram. Otherwise it is checked whether the reporting limit is exceeded. In this case the identity is finally checked by comparing full scan sample UV spectra with full scan standard UV spectra.

## 7.8 Quality Assurance

Before loading the test chamber, a blank check of the empty chamber is performed and compliance with background concentrations in accordance with EN 16516 / ISO 16000-9 is determined.

Air sampling at the chamber outlet and subsequent analysis is performed in duplicate. Relative humidity, temperature and air change rate in the chambers is logged every 5 minutes and checked daily. A double determination is performed on random samples at a regular interval and results are registered in a control chart to ensure the uncertainty and reproducibility of the method.

The results are only valid for the tested sample(s).

This report may only be copied or reprinted in its entirety, parts of it only with a written acceptance by Eurofins.

The stability of the analytical system is checked by a general function test of device and column, and by use of control charts for monitoring the response of individual substances prior to each analytical sequence.

## 7.9 Accreditation

The testing methods described above are accredited on line with EN ISO/IEC 17025 by DANAK (no. 522). This accreditation is valid worldwide due to mutual approvals of the national accreditation bodies (ILAC/IAF, see also [www.eurofins.com/galten.aspx#accreditation](http://www.eurofins.com/galten.aspx#accreditation)).

Not all parameters are covered by this accreditation. The accreditation does not cover parameters marked with an asterisk (\*), however analysis of these parameters is conducted at the same level of quality as for the accredited parameters.

## 7.10 Uncertainty of the Test Method

The relative standard deviation of the overall analysis is 22%. The expanded uncertainty  $U_m$  equals  $2 \times RSD$ . For further information please visit [www.eurofins.dk/uncertainty](http://www.eurofins.dk/uncertainty).

## 7.11 Decision Rules

Eurofins Product Testing A/S, declare statement of conformity based on the “Binary Statement for Simple Acceptance Rule” described in ILAC’s “Guidelines on decision Rules and Statements of Conformity” ILAC-G8:09/2019.

This means that results are evaluated with the same number of significant digits as limit / acceptance values, and declaration of conformity is based on results being less than or equal to limit / acceptance values.

For limit values with more than two significant digits, the third digit will be used to confirm whether a result is below or equal to the limit value. It will always be indicated in the evaluation table if this expanded evaluation is performed.

For further information please visit [www.eurofins.dk/product-testing/om-os/beslutningsregler/](http://www.eurofins.dk/product-testing/om-os/beslutningsregler/)

## 7.12 Version History

Report date	Report number	Modification
16/06/2025	392-2025-00203101_C_EN	Current version